



**Bs-Temperature**

H=1194A/m



Initial permeability $\mu_i$	25°C	2500±25%
Saturation magnetic flux density $B_s$ (mT)	25°C	520
flux density	1194A/m	100°C 420




Temperature(°C)

Curie temperature Tc(°C) ≥220

Electrical resistivity  $\rho(\Omega\cdot m)$  3

Density  $\rho(g/cm^3)$  4.8×10<sup>3</sup>

**$\mu_i$ -Temperature**



Test core : Toroid(mm)


OD : 25

ID : 15

H : 7.5

Initial permeability

**$\mu_i$ -Frequency**



**B-H**

